



ARDEX MC™ RAPID

One-Coat Moisture Control System For Concrete to Receive ARDEX Underlayments

One-coat epoxy resin system

**No sand broadcast required for underlayment applications
of 1/4" (6 mm) or less**

Ready to prime in just 4 hours

Solvent free, alkali resistant

Tenacious bond to substrate

**Reduces vapor emissions to below maximum acceptable levels
for floor coverings**

For RH readings up to 100%

ASTM E96 perm rating \leq 0.10

**Use under all standard commercial and residential floor coverings on
interior substrates only**

ARDEX Engineered Cements
400 Ardex Park Drive
Aliquippa, PA 15001 USA
Tel: 724-203-5000
Toll Free: 888-512-7339
Fax: 724-203-5001
www.ardexamericas.com

ARDEX MC™ RAPID

One-Coat Moisture Control System for Concrete to Receive ARDEX Underlayments

Description and Usage

The ARDEX MC™ RAPID MOISTURE CONTROL SYSTEM is a one-coat, 100% solids epoxy moisture management system formulated to suppress excessive moisture vapor emissions in new or existing concrete prior to installing an ARDEX underlayment with flooring. It is especially suited to treat areas of new concrete in critical installations, such as health care and institutional applications where the construction schedule does not allow adequate drying of the concrete. ARDEX MC RAPID is also recommended over existing concrete where the level of moisture emissions from the slab exceeds the maximum allowed by the manufacturer of the finished floor covering. Designed specifically for fast-track installations, ARDEX MC RAPID can be primed to receive an ARDEX underlayment in as little as 4 hours.

The ARDEX MC RAPID system is based on a reactive epoxy that produces a hard surface and tenaciously bonds to the substrate. Once cured, ARDEX MC RAPID is able to reduce any level of moisture emissions to an acceptable level, even over new concrete that is only 7 days old. No sand broadcast is used for underlayment layers of 1/4" (6 mm) thick or less. For thicker applications, apply a second coat of ARDEX MC RAPID with a sand broadcast, or use the ARDEX MC™ PLUS MOISTURE CONTROL SYSTEM or the ARDEX MC™ ULTRA MOISTURE CONTROL SYSTEM.

Moisture Testing

Prior to beginning the installation, measure the relative humidity within the concrete in accordance with ASTM F2170. When installed in accordance with our written recommendations, ARDEX MC RAPID is suitable for moisture levels up to 100% RH.

Please note that very high RH levels (above 98%) could be indicative of external water infiltration from inadequate drainage, leaks, broken pipes, etc. Verify that all external sources of water are controlled sufficiently prior to installation.

The surface of the concrete must be completely dry at the time the ARDEX MC RAPID is installed. For RH levels above 98%, verify concrete surface dryness by mat testing in conformance with ASTM D4263. The test must be conducted for at least 4 hours, which is the time required for ARDEX MC RAPID to be set sufficiently. To ensure that condensation does not form, it is extremely important to check the surface temperature of the concrete just prior to installation to verify that this temperature is at least 5°F (3°C) higher than the dew point for the given temperature and humidity in the space and rising. For example, if the dew point temperature in the space is 60°F (16°C), the slab temperature must be 65°F (19°C) or higher and rising.

Substrate Preparation

All concrete substrates must be structurally sound and solid, surface dry and thoroughly clean and free of oil, wax, grease, asphalt, paint, latex compounds, curing and sealing compounds and any contaminant that could act as a bond breaker. The concrete must have a minimum tensile strength of 150 psi (1.03 N/mm²) for areas to receive normal foot traffic and 200 psi (1.38 N/mm²) for areas of heavy commercial traffic when tested in accordance with ASTM C1583.

Mechanical preparation of the surface is required to obtain a minimum ICRI concrete surface profile of 3 (CSP 3). Substrate preparation must be by mechanical means, such as shot blasting. Broom sweep and vacuum the prepared surface. Acid etching, solvents, sweeping compounds, adhesive removers and sanding are not acceptable means of cleaning the substrate.

If the concrete substrate is too uneven to provide a uniform film thickness of the ARDEX MC RAPID (typically CSP 6 or higher), the substrate can be pre-smoothed using ARDEX K 301™ SELF-LEVELING EXTERIOR CONCRETE TOPPING or ARDEX MRP™ MOISTURE RESISTANT PATCH. Please refer to the appropriate ARDEX technical brochure for installation instructions and necessary cure times.

Recommended Tools

Epoxy mixing paddle, low speed drill, short-nap paint roller or notched squeegee (smoother surfaces), long-nap paint roller (more uneven surfaces) and a paintbrush.

Dormant Cracks and Dormant Saw Cut Joints

To achieve a continuous moisture barrier, ARDEX recommends the use of a two-part, low viscosity, 100% solids, rigid crack and joint filler, such as ARDEX ARDIFIX™, to fill small, non-moving cracks and non-moving saw cuts in existing concrete substrates. Cracks greater than a hairline in width (1/32" / 0.79 mm) and saw cuts must be filled in strict accordance with the installation instructions provided by the ARDEX Technical Service Department. Once the dormant cracks and dormant saw cuts have been filled properly, broadcast sand to refusal, and allow these areas to cure thoroughly prior to proceeding with the ARDEX MC RAPID installation.

Moving Joints and Moving Cracks

All moving joints and moving cracks must be honored up through the ARDEX MC RAPID, the ARDEX underlayment and the floor covering by installing a fully flexible sealing compound designed specifically for use in moving joints, such as ARDEX ARDISEAL™ RAPID PLUS.

ARDEX cannot be responsible for issues arising from expansion and isolation joints, saw cuts or new or existing cracks that may develop, widen or become more narrow after the system has been installed.

For questions regarding the appropriateness of specific joint treatment compounds, please contact the ARDEX Technical Service Department at 888-512-7339.

Mixing and Application

Each individual unit of ARDEX MC RAPID comes in a 22 lb. (10 kg) unit containing separate, pre-measured quantities of hardener (Part B) and resin (Part A). After opening each container, stir the individual components thoroughly before blending. The hardening agent (Part B) is added to the resin (Part A). Pour all of the hardener into the resin portion, and mix thoroughly for a minimum of 3 minutes using a low speed drill and an epoxy mixing paddle. Once mixed, pour some of the epoxy back into the hardener container, mix for 10 seconds, and then pour all of the contents back into the resin container. Mix for an additional 30 seconds before applying.

Apply the freshly mixed ARDEX MC RAPID to the prepared concrete surface in a uniform direction at a maximum application rate of 270 sq. ft. (25 sq. m) per unit (approx. 10 mils / 250 microns). Use a short-nap paint roller or notched squeegee with back-rolling for smoother surfaces, and a longer nap roller for more uneven substrates. To minimize the potential for pinhole formation, work the ARDEX MC RAPID into the surface with the roller to ensure maximum penetration. ARDEX MC RAPID can also be worked into the surface with a paintbrush for hard to reach areas and corners. Once an area has been coated completely, allow this to dry for a minimum of 4 hours (max. 24 hours).

For ARDEX underlayment applications of 1/4" (6 mm) or less, prime the surface of the ARDEX MC RAPID with ARDEX P 82™ ULTRA PRIME. Allow the ARDEX P 82 to dry thoroughly (min 3 hours; max 24 hours) before installing the underlayment.

For underlayment installations greater than 1/4" (6 mm), or, if the ARDEX MC RAPID was not worked into the surface sufficiently enough to prevent pinholes, you must apply another coat of ARDEX MC RAPID with a sand broadcast. No ARDEX P 82 is required. Apply the second coat of ARDEX MC RAPID at a 90° angle to the direction the first coat was applied. While this coat is still in a fresh state (maximum 20 minutes), broadcast an excess of fine sand (less than 1/50" in grain size or 98.5% passing sieve size #30 or #35) consistently over the entire area. When broadcasting the sand, use a NIOSH-approved dust mask

in conformance with OSHA requirements regarding the handling of sand. Do not stand or walk on the freshly applied epoxy when broadcasting the sand. Once an area has been covered completely with sand, the surface of the sand can be walked on, being careful not to expose the epoxy at any time. Use approximately 1 lb. of sand per sq. ft. of area. Once the sand broadcast is complete, avoid all general traffic over the surface for a minimum of 4 hours.

After 4 hours, broom sweep and vacuum the surface to remove all loose sand. The clean, prepared surface of the sand is the priming system for the ARDEX underlayment. No additional priming is required. There is no limit to how long the sanded surface can remain open before installing the ARDEX underlayment provided that the surface does not become contaminated. If the underlayment will not be installed immediately, protect its surface from construction traffic, dirt and debris using Masonite or similar. Install the ARDEX underlayment in accordance with the printed instructions found in the corresponding ARDEX technical brochure.

It is not necessary to re-test the substrate for moisture emissions prior to installing the floor covering.

Notes

FOR PROFESSIONAL USE ONLY.

The installation of ARDEX MC RAPID does not require calcium chloride testing of the concrete per ASTM F1869, nor does ASTM permit this test over the top of concrete that has been treated with a moisture remediation system. ARDEX MC RAPID is warranted to reduce emissions to an acceptable level for the entire flooring system, regardless of the values obtained by this test.

ARDEX MC RAPID has a working time of approximately 20 minutes at 70°F (21°C). Lower temperatures will lengthen the working time, while higher temperatures will shorten it dramatically. Do not apply ARDEX MC RAPID if the surface temperature is below 50°F (10°C).

Once the ARDEX MC RAPID is mixed thoroughly, use it immediately and without interruption. Due to its high reactivity, this epoxy has a tendency toward intense heat buildup, especially when left in the original container. If this occurs, do not touch the container. Close the lid loosely and transport the container by the handle to a cool room or outdoors until it sets and cools.

Precautions

Carefully read and follow all precautions and warnings on the product label. For complete safety information, please refer to the Material Safety Data Sheet (MSDS) available at www.ardexamericas.com.

Technical Data According to ARDEX Quality Standards

All data based on 70°F (21°C) installation temperatures. Physical properties are typical values and not specifications.

Mixing Ratio:	Add entire pre-measured contents of Part B (hardener) into Part A (resin).
Coverage on CSP 3 Prepared Concrete:	Max. 270 sq. ft. (25 sq. m) per mixed unit of ARDEX MC RAPID (Will vary with surface profile)
Permeability (ASTM E96):	1 coat at 10 mils - 0.06 perms 2 coats, each at 10 mils with sand in 2nd coat - 0.06 perms
Effect of 14 pH Solution (ASTM D1308):	No effect
Working Time:	20 minutes
Pot Life:	20 minutes
Walkable:	4 hours
Prime and install underlayment:	Min. 4 hours Max. 24 hours
VOC:	0 g/L (calculated and reported, SCAQMD 1113)
Packaging:	One 22 lb. (10 kg) unit
Storage:	Store in a cool dry area. Do not leave containers exposed to sun. Keep from freezing. Keep away from heat.
Shelf Life:	1 year, if unopened

Warranty:

ARDEX Engineered Cements Standard Limited Warranty applies. Extended system warranty is available. Please note that training by the ARDEX Technical Service Department is required for extended warranty eligibility. Please contact the ARDEX Technical Service Department for details.

© 2012 ARDEX, L.P. All rights reserved.
AT301 (09/20/12)

ARDEX Engineered Cements
400 Ardex Park Drive
Aliquippa, PA 15001 USA
Tel: 724-203-5000
Toll Free: 888-512-7339
Fax: 724-203-5001
www.ardexamericas.com